



**FTG**  
safety shoes

Class: S3 SRC  
Sizes: 35-48  
Instep: 11  
Weight( $\pm 10\%$ ): 570 gr. (\*)

## TECHNICAL SHEET ART. BETA

**Description** low shoe in black leather, 100% polyester lining, FTG Comfort insole, extractable and washable, polyurethane sole, bending resistant, abrasion resistant, oil resistant, slip resistant, antistatic

**Suggested sectors of usage** Building/construction, utilities, naval industry, mineral industry, cooperative society

**Care and maintenance** clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirement
<b>Toe cap:</b> steel toe cap, impact resistant 200 J	5.3.2.3 5.3.2.4	Impact resistance Compression resistance	mm mm	14,5 14,0	>= 14 >= 14
<b>Midsole:</b> non metallic HRP Insole with high tenacity fibres layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100	>= 1.100
<b>Antistatic footwear:</b> dissipation capacity of the electrostatic charge	6.2.2.2	Electric resistance - Wet - Dry	Mohm Mohm	951,0 1000,0	>= 0,1 <= 1000
<b>Capacity of energy absorption in the heel area</b>	6.2.4	Energy absorption in the heel area	J	35,0	>= 20
<b>Upper:</b> leather, black color, thickness 2.0 mm	5.4.6 5.4.3	Water vapour permeability Coefficient of permeability Tearing Strength	mg/cm <sup>2</sup> h mg/cm <sup>2</sup> N	1,3 19,6 208	>= 0,8 >= 15 >= 120
<b>Vamp lining:</b> non woven textile for toe cap, grey color	5.5.3 5.5.1 5.5.2	Water vapour permeability Coefficient of permeability Tearing Strength Abrasion resistance (dry) Abrasion resistance (wet)	mg/cm <sup>2</sup> h mg/cm <sup>2</sup> N cycles cycles	3,4 30,2 30 no rupture no rupture	>= 2 >= 20 >= 15 25.600 12.800
<b>Quarter lining:</b> 100% honeycomb finished polyester, breathable, abrasion resistant, red color	5.5.3 5.5.1 5.5.2	Water vapour permeability Coefficient of permeability Tearing Strength Abrasion resistance (dry) Abrasion resistance (wet)	mg/cm <sup>2</sup> h mg/cm <sup>2</sup> N cycles cycles	6,8 54,4 25 no rupture no rupture	>= 2 >= 20 >= 15 51.200 25.600
<b>Insole lining:</b> textile anti perforation midsole HRP insole	5.7.3	Water Absorption Ability to release water	Mg/cm <sup>2</sup>	78 99%	>= 70 >= 80%
<b>Sole:</b> monodensity polyurethane, bending resistant, abrasion resistant, oil resistant, slip resistant, antistatic	5.8.2 5.8.3 5.8.4 5.8.5 6.4.2 5.11	Tearing Strength Abrasion resistance Bending resistance Hydrolysis Hydrocarbons resistance (volume increase) Slip resistance on ceramic floor with water and detergent Slip resistance on steel floor with glycerine	kN/m mm <sup>3</sup> mm mm % flat inclined flat inclined	5,5 98 3,0 2,0 0,2 0,40 0,35 0,18 0,13	>= 5 <= 250 <= 4 <= 6 <= 12% >= 0,32 >= 0,28 >= 0,18 >= 0,13

Azo dye free: no presence of azo dye forbidden by normative 1907/2006/CE Attachment XVII (method UNI EN 14362-1:2004 – Textile)

(\*) = Indicative weight that refers to 1/2 pair in size 42