

EN ISO 20345:2022

Class: S1PS FO SR Sizes: 38-47

Instep: 12

Weight (±10%): **550 gr**. (*)

TECHNICAL SHEET ART. RELAY

Description: low shoe in black MESH, with HIGH-TEX inserts, 100% polyester lining, non-metallic HRP Insole, SPORT-LITE insole, anatomic, antistatic, antibacterial and ESD, double density polyurethane sole, bending resistant, abrasion resistant, oil resistant, slip resistant, ESD **Suggested sectors of usage:** Building / Construction, Electronics / Electrotechnics, Mechanical

industry, Servicing, Logistics / Packaging, Professionals / Craftsmen

Care and Maintenance: clean periodically the outsole and the upper with non-aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source



Complete shoe	Norm	Description	Unit	Results	EN ISO 20345 requirements
Toe Cap: non-metallic toe cap THIN CAP, impact resistant 200 J	5.3.2.6	Impact resistance	mm	15	≥ 14
	5.3.2.7	Compression resistance	mm	17,5	≥ 14
Midsole: non-metallic HRP Insole with high tenacity fibres multi layers, polyester	6.2.1	Perforation resistance (single value)	N	1.032	≥ 950
composition, perforation resistant		Average value		1.224	≥ 1.100
ESD footwear : dissipation capacity of the electrostatic charge	EN ISO 61340-5-1	Electrical resistance for ESD footwear	Mohm	44	≤ 100
Capacity of Energy Absorption in the heel area	6.2.4	Energy absorption in the heel area	J	29,5	≥ 20
Upper: MESH, HIGH-TEX inserts, black color	5.4.6	Water vapour permeability	mg/cm² · h	48,5	≥ 0,8
		Water vapour coefficient	mg/cm ²	388,2	≥ 15
	5.4.3	Tear strength	N	189	≥ 60
Vamp/Quarter Lining : honeycomb 100% finished polyester, breathable, abrasion resistant, black colour + green colour	5.5.4	Water vapour permeability	mg/cm² · h	132,3	≥ 2
		Water vapour coefficient	mg/cm ²	1058,7	≥ 20
	5.5.2	Tear strength	N	43,5	≥ 15
	5.5.3	Abrasion resistance (dry)	cycles	no holes	25.600
		Abrasion resistance (wet)	cycles	no holes	12.800
Sole : double density polyurethane sole, bending resistant, abrasion resistant, oil	5.8.3	Tear strength	kN/m	7,2	≥ 8
resistant, slip resistant, ESD	5.8.4	Abrasion resistance (black)	mm³	33	≤ 150
	5.8.5	Bending resistance	mm	0	≤ 4
	5.8.6	Hydrolysis	mm	0	≤ 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	1,9%	≤ 12%
	6.2.10	Slip resistance on ceramic glycerine (SR)	heel forward (7°)	0,22	≥ 0,19
			tip back (7°)	0,23	≥ 0,22