



EN ISO 20345:2022

Class: S3S HI CI HRO FO  
 Sizes: 38-48  
 Instep: 12  
 Weight (±10%): **780 gr.** (\*)

## TECHNICAL SHEET ART. HERMES

**Description:** low shoe in black leather, 100% polyester lining, non-metallic HRP Insole, ATOMIC insole, anatomic and breathable, dual component in polyurethane and rubber sole, bending resistant, abrasion resistant and oil resistant

**Suggested sectors of usage:** Farming / Zootechnics, Cold Environment, Building / Construction, Mechanical industry, Mineral Industry, Naval Industry, Petrochemical Industry, Oil & Gas Industry, Utilities, Steel Industry / Foundries

**Care and Maintenance:** clean periodically the outsole and the upper with non-aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
<b>Toe Cap:</b> Non-metallic toe cap TOP COMPOSITE, impact resistant 200 J	5.3.2.6	Impact resistance	mm	19,5	≥ 14
	5.3.2.7	Compression resistance	mm	18,0	≥ 14
<b>Midsole:</b> non-metallic HRP Insole with high tenacity fibres multi layers, polyester composition, perforation resistant	6.2.1	Perforation resistance single value	N	1.458	≥ 950
		Average value		1.314	≥ 1.100
	5.7.3	Water absorption	mg/cm <sup>2</sup>	95,7	≥ 70
		Water desorption		96,2%	≥ 80%
<b>Capacity of Energy Absorption in the heel area</b>	6.2.4	Energy absorption in the heel area	J	43	≥ 20
<b>Upper:</b> grain leather, black + blue color	5.4.6	Water vapour permeability	mg/cm <sup>2</sup> · h	2,0	≥ 0,8
		Coefficient of permeability	mg/cm <sup>2</sup>	18,7	≥ 15
	5.4.3	Tearing Strength	N	118	≥ 60
<b>Vamp/Quarter Lining:</b> honeycomb 100% finished polyester, breathable, abrasion resistant, gray colour	5.5.4	Water vapour permeability	mg/cm <sup>2</sup> · h	119,6	≥ 2
		Coefficient of permeability	mg/cm <sup>2</sup>	978,7	≥ 20
	5.5.2	Tearing Strength	N	33,3	≥ 15
	5.5.3	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
<b>Sole:</b> dual component in polyurethane and rubber sole, bending resistant, abrasion resistant, oil resistant	5.8.3	Tearing Strength	kN/m	20,5	≥ 8,0
	5.8.4	Abrasion resistance	mm <sup>3</sup>	105	≤ 150
	5.8.5	Bending resistance	mm	0,2	≤ 4
	5.8.6	Hydrolysis	mm	0	≤ 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	7,0%	≤ 12%
	6.2.3.1	Warm Insulation of the Sole (HI)	°C	8,5	≤ 22
	6.2.3.2	Cold Insulation of the Sole (CI)	°C	3,5	≤ 10

In model HERMES and its components there is no presence of dangerous substances by Annex XVII to regulation no. 1907/2006/CE and subsequent amendments and additions

(\*) = Indicative weight that refers to 1/2 pair in size 42