



Class: S3 SRC
 Sizes: 36-48
 Instep: 12
 Weight(±10%): 728 gr. (*)

TECHNICAL SHEET ART. FOKKER

Description Boot in grain leather beige TOP LEATHER, inlined, non-metallic insole lining HRP INSOLE, Atomic insole, anatomic and ESD, double density polyurethane sole, bending resistant, abrasion resistant, oil resistant, slip resistant, ESD

Plus Midsole compound particularly studied to get a soft PU density for a higher comfort

Suggested sectors of usage Building/costruction, petrochemical industry, oil & gas industry, naval industry , mineral Industry , professional/ craftsman

Care and Maintenance Clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirement
Toe cap: Top Composite toe cap, impact resistant 200 J	5.3.2.3	Impact resistance	mm	15,5	>= 14
	5.3.2.4	Compression resistance	mm	15,0	>= 14
Midsole: non metallic HRP Insole with high tenacity fibres layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100	>= 1.100
ESD footwear: dissipation capacity of the electrostatic charge	EN ISO 61340-5-1	Electric resistance Class 2	Mohm	22,0	< 35
Capacity of energy absorption in the heel area	6.2.4	Energy absorption in the heel area	J	32,0	>= 20
Upper: grain leather beige, thickness 2,0 mm	5.4.6	Water vapour permeability	mg/cm ² h	1,4	>= 0,8
		Coefficient of permeability	mg/cm ²	15,7	>= 15
	5.4.3	Tearing Strength	N	199	>= 120
Vamp lining: Non woven textile for toe cap, grey color	5.5.3	Water vapour permeability	mg/cm ² h	3,4	>= 2
		Coefficient of permeability	mg/cm ²	30,2	>= 20
	5.5.1	Tearing Strength	N	30	>= 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
Insole lining: textile anti perforation midsole HRP Insole	5.7.3	Water Absorption	Mg/cm ²	78	>= 70
		Ability to release water		99%	>= 80%
Sole: Double density polyurethane, bending resistant, abrasion resistant, oil resistant, slip resistant, ESD	5.8.2	Tearing Strength	kN/m	11,5	>= 8
	5.8.3	Abrasion resistance	mm ³	50	<= 150
	5.8.4	Bending resistance	mm	1,5	<= 4
	5.8.5	Hydrolysis	mm	2,5	<= 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	-0,6%	<= 12%
	5.11	Slip resistance on ceramic floor with water and detergent	flat	0,43	>= 0,32
			inclined	0,40	>= 0,28
		Slip resistance on steel floor with glycerine	flat	0,21	>= 0,18
			inclined	0,15	>= 0,13

Fokker style and its components: no presence of dangerous substances by Annex VII to regulation no. 1907/2006/CE and subsequent amendments and additions

(*) = Indicative weight that refers to ½ pair in size 42